

PENNASOL High Pressure Gear Oil GL 3

PENNASOL High Pressure Gear Oil GL 3 is characterized by good lubricating properties and top viscosity-temperature behaviour. PENNASOL High Pressure Gear Oil GL can be used in industrial gears, such as spur and bevel gears, without offset axes, in worm gears and for lubricating sliding parts.

ACEA-/API-specifications:

- API GL 3

Parameter	Unit	Testing method	PENNASOL HIGH PPRESSURE GEAR OIL GL 3		
			SAE 80W	SAE 90	SAE 140
Density 15°C	kg/m ³	DIN EN ISO 12185	872	885	900
Flash point COC	°C	DIN ISO 2592	226	228	230
Pour point	°C	DIN ISO 3016	- 27	- 24	- 21
Viscosity 40°C	mm ² /s	DIN 51562-1	66,7	150	450
Viscosity 100°C	mm ² /s	DIN 51562-1	9.0	15.5	32.0
VI		DIN ISO 2909	109	105	103

06/2015

Version 3

The given data are typical data. Please observe operating prescriptions.



Motorenöle <i>Motor oils</i>	Getriebeöle <i>Gear oils</i>	Zweitaktöle und Traktorenöle <i>Two-stroke oils and tractor oils</i>	Hydrauliköle <i>Hydraulic oils</i>	Industrie- und Spezialschmierstoffe <i>Industrial and specialty lubricants</i>
--	--	--	--	--

Available packaging:

	Bulk	965 Liter	208 Liter	60 Liter	20 Liter	4 * 5 Liter	12 * 1 Liter	Notes:
PENNASOL HIGH PRESSURE GEAR OIL GL 3	•	•	•	•	•			

PENNASOL High Pressure Gear Oil GL 3¹

¹ This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either AVISTA OIL Group or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale.